

Radionuclide Release from Savannah River Site Tank 18 Waste Residual Solids under Conditions Anticipated Following Tank Closure-17450

William D. King, Mark H. Layton and David T. Hobbs
Savannah River National Laboratory and Savannah River Remediation, Aiken, SC;

ABSTRACT

Leaching studies have been conducted with actual Savannah River Site High Level Waste Tank 18 residual radioactive sludge and grout-representative solids in pore water simulants targeting solution pH and E_h values anticipated during aging of the closed tank. Soluble metal concentrations in the leachate solutions observed after several weeks were consistent with simulant test results. The lowest concentrations for all metals were observed under reducing conditions (~ -200 mV) at an average pH of 11.2. The highest uranium, neptunium, and plutonium concentrations during leaching studies were observed at average pH and E_h values of 9.4 and +506 mV, respectively. The highest technetium concentrations were observed under oxidizing conditions at E_h values ranging from +325 to +520 mV and pH values ranging from 9.3 to 11.2. The maximum metal concentrations observed during leach testing for neptunium, plutonium, and technetium were all near or below the maximum predicted values, while uranium concentrations exceeded predictions. For oxidizing test conditions, the residual sludge samples were pre-washed with pore water simulants to reduce the pH prior to initiating the leaching tests. Higher metal concentrations were observed for the wash solutions than were observed for any leach test sample and the concentrations of the actinides significantly exceeded the predicted values. Mass balance calculations indicated that most of the uranium dissolved from the oxidizing test samples during washing, while <20% of each of the other elements dissolved. The new data from the Tank 18 leaching studies is not expected to significantly impact predicted doses from the release of radionuclides into the environment from the closed waste tank based on solubility assumptions used in previous Performance Assessment modeling.

INTRODUCTION

Current practice for closing High Level Waste (HLW) tanks at the Savannah River Site (SRS) involves removing waste to the maximum extent practical using mechanical sluicing methods, disconnecting all transfer lines and penetrations into the tank, and filling the internal volume of the tank with grout (concrete). As of March 2017, Savannah River Remediation has closed SRS Tanks 5, 6, 12, 16, 17, 18, 19, and 20. Performance Assessment (PA) modeling of the release of radionuclides from residual waste solids in these tanks into the environment over extended time periods indicated that uranium, neptunium, plutonium, and technetium are among the most likely risk

drivers for environmental contamination [1]. The PA and supporting waste release modeling indicated that plutonium release from SRS Tank 18 residuals (which contained relatively high Pu concentrations) was highest during the tank aging period identified as Oxidizing Region III, which was predicted to occur after >2,120 pore volumes of grout pore water have passed through the system. At this stage, the dominant grout phase is expected to be calcite (CaCO₃). (Note: Grout pore water is defined as natural infiltrating groundwater exposed to the grout fill material and the residual waste solids layer within the closed tank environment. Furthermore, a pore volume represents the total volume of the pore voids within the grout fill material inside the closed tank.)

In order to support SRS tank closure efforts, a test methodology was developed using simulated sludge waste solids, grout-representative solid reagents, and grout pore water solutions (based on SRS groundwater compositions) to produce slurries representing tank residuals and conditions following closure [2, 3]. Solution pH and E_h (Oxidation Reduction Potential versus the Standard Hydrogen Electrode) values were targeted which are expected (based on PA modeling) during the various aging periods following waste tank closure [4]. The initial pore water condition (Reducing Region II) was predicted to have an E_h of -0.45 V and a pH of 11.1. The pore water is expected to become increasingly oxidizing and less basic with increasing time and pore water throughput. The second aging period (Oxidizing Region II) was predicted to have an E_h of +0.56 V and a pH of 11.1. The final aging period following tank closure (Oxidizing Region III) was predicted to have an E_h of +0.68 V and a pH of 9.2. The target conditions for each aging period are summarized in Table I. The target E_h values under oxidizing conditions assume equilibrium with dissolved oxygen.

TABLE I. Target SRS Tank 18 Pore Water Conditions.

Target Condition	E _h (mV)	pH
Reducing Region II	-470	11.1
Oxidizing Region II	+560	11.1
Oxidizing Region III	+680	9.2

The equipment designed and the test methodology developed to conduct the leach testing were successfully utilized to evaluate the metal solubilities and leaching characteristics of actual SRS Tank 18 residual sludge solids, although the target minimum and maximum E_h values were not achieved in simulated or actual waste testing. This testing was conducted remotely within the Savannah River National Laboratory (SRNL) Shielded Cells facility. The equipment was designed for remote

operation and a sampling system and methodology were utilized to rigorously exclude residual radionuclides present in the shielded cells environment from contaminating the test samples. This approach should be suitable for leach testing of other SRS waste tank residual materials within this test facility.

EXPERIMENTAL DETAILS

Customized glass test vessels of various types were prepared for leach testing in the SRNL shielded cells. All test vessels were made of 70.2 mm ID glass tubing and the main portions of the vessels were ~8 cm tall. The vessels fit snugly into sample slots in the top of a customized water bath. The water bath was positioned over two multi-position stir plates and leach sample agitation during testing was accomplished using magnetic stir bars placed in the test vessels. A water recirculator was utilized for temperature control with a set temperature of 22.1 °C. Individual sample temperatures were measured using a K-type thermocouple near the end of testing and all samples were found to be 21 °C. A customized water bubbler manifold was constructed and attached to the back of the water bath in order to monitor and control gas flow through each individual sample vessel during testing. Low gas supply pressures (typically <5 PSI or <34 kPa) were utilized to purge the test vessels. Gas flow control through the vessels was accomplished on the downstream side of each sample line by the adjustment of stainless steel Swagelok needle valves. Because the gas outlet lines for each sample were open to the bubbler, the gas pressures in the samples were slightly above atmospheric pressure during testing.

Three types of glass vessels were prepared for testing including: caustic scrubber, humidifier, and leach sample vessels. Upper vessel attachments were made from #7 and #15 internal glass screw threads. Threaded Teflon fittings for the screw threads were modified to accommodate the various needed connections.

The purpose of the caustic scrubber vessels was to remove carbon dioxide gas from the air supply lines through gas contact with 5 M NaOH solution to avoid impacting the test slurry pH during air purging. Each scrubber vessel included a gas supply line consisting of a 12 mm OD fritted glass gas dispersion tube to promote the formation of numerous gas bubbles and high gas/liquid contact. A second port with a magnetized cap was included in the scrubber vessel top for the addition of sodium hydroxide reagent. The third and final scrubber vessel attachment included a stainless steel demister suspended within a short glass column for the removal of entrained solution from the outlet gas. Scrubber vessels were not needed for reducing test conditions. When utilized, the caustic scrubbers were the first vessels that the air was passed through and the gas was then transferred to a humidifier vessel.

Downstream vessels included the humidifier and leach test vessels. The purpose of the humidifier vessels was to saturate the supply gas with water vapor at the sample

temperature and minimize leach sample evaporation during testing. For oxidizing conditions, the humidifier vessels also served to isolate the leach test samples from the caustic scrubber solution. A single humidifier vessel was utilized to treat the supply gas for each sample type with the water-saturated gas stream then being split between two leach test vessels. Each humidifier vessel included a gas supply line consisting of 6.4 mm (¼ inch) OD thin wall polyethylene tubing which had been heat-sealed at the end. Multiple 0.40 mm (1/64 inch) holes were drilled into the sides of the tubing near the bottom to produce bubbles and promote gas-liquid contact. The humidifier vessels also included a water addition port with a magnetized cap and two gas outlet lines containing demisters. The outlet lines led to the leach test vessels. The glass leach sample vessels included a gas supply port, a sample/reagent addition port (magnetized cap), and a single gas outlet connection identical in design to the humidifier vessels. The sample addition port was also used to insert the pH and ORP probes during measurements.

Gases were passed through a series of vessels for treatment to produce the desired sample conditions. The vessels in a given series were connected using 3.2 mm (1/8 inch) ID Tygon tubing with quick-connect fittings on each end to allow for vessel detachment, removal, or reconfiguration during testing. The sample vessel gas outlet lines were connected to the bubbler system using the same tubing. Control vessels for each sample type were also incorporated into the system. CO₂-stripped air was used as the baseline purge gas for the oxidizing samples. During periods when carbon dioxide was needed to lower the pH, the caustic scrubber was removed from the sequence of vessels that the air was passed through until the target pH was reached. Ultra-high purity nitrogen gas was used as the purge gas for the reducing samples throughout testing.

Based on the simulant studies and the expected solubilities of most of the metals, it was anticipated that very low metal concentrations near analysis detection limits would be observed [3]. The need to measure very low concentrations was especially problematic for plutonium, since plutonium contamination of samples in the shielded cells is known due to high background plutonium levels within the facility. As a result, a sub-sampling system and methodology were developed to allow for the isolation of filtered samples in the analysis bottles without contamination.

The sub-sampling system involved modified, plastic shielded analysis bottles with caps containing 6.4 mm (¼ inch) OD polyethylene tubing and quick-connect attachments. The sampling system included a syringe with a directly-attached filter. Tubing (3.2 mm or 1/8 inch ID) was attached to the downstream side of the filter with a male quick-connect fitting attached to the other end of the tubing. The filter end of the sub-sampling unit was covered with a small plastic bag to minimize the possibility of post-filtration contamination in the cell. The bag was removed just prior to sampling and the syringe filter unit was attached directly to the analytical bottle

via the quick-connect fitting. A separate vent line containing a quick-connect fitting and an in-line filter was also attached to the analysis bottle during sub-sampling to prevent sample contamination through the vent line from plutonium dust. Using this system, the analysis sub-samples were removed from the leach test vessels using a plastic slurry and transferred into the top of the syringe barrel after removing the plunger. In addition, prior to testing, the cell floors were wiped clean, and prior to each sampling event, clean disposable cloth wipes were laid down on the cell floor to minimize contamination.

Outside of the shielded cells environment, a synthetic infiltration water simulant based on the average composition observed for groundwater collected from non-impacted wells within the SRS water table aquifer was developed and prepared from ultrapure water and reagent grade chemicals (composition provided in Table II). Tank 18 grout pore water simulants were prepared from the infiltration water for each condition shown in Table I with an initial focus on achieving the target pH values of 11.1 (Reducing Region II and Oxidizing Region II) and 9.2 (Oxidizing Region III). The higher pH (11.1) pore water simulant was prepared from the infiltration water by adding CaCO_3 reagent to saturation and $\text{Ca}(\text{OH})_2$ reagent until the target pH was achieved. The lower pH (9.2) pore water simulant was prepared from the infiltration water by the addition of CaCO_3 to saturation (no calcium hydroxide addition). This resulted in a solution containing trace amounts of CaCO_3 solids with a pH near 10. Subsequent, brief (~15 minutes) purging of the solution with air resulted in the absorption of CO_2 and a reduction of the solution pH to near 9.

TABLE II. As-Prepared Composition of Infiltration Water Simulant Based on SRS Groundwater.

Ion	Concentration (mg/L)
Na^+	1.39
K^+	0.21
Mg^{2+}	0.66
Ca^{2+}	1.00
Cl^-	5.51
SO_4^{2-}	0.73

All of the as-prepared simulants had solution E_h values near +500 mV. Solutions for reducing and oxidizing test cases were subsequently purged with high purity nitrogen and CO_2 -stripped air, respectively. For the Reducing Region II case, overnight nitrogen purge resulted in a solution E_h value near -100 mV. Subsequent addition of reagent grade ferrous sulfide (FeS) solids to the nitrogen-purged solution resulted in an E_h value near -200 mV. Analysis revealed that these preparations result in elevated calcium concentrations (measured values 7-28 mg Ca/L) relative to the initial infiltration water simulant (1 mg Ca/L).

These simulants were transferred into the SRNL Shielded Cells facility and used for leach test sample preparations. Known volumes of the simulants were transferred into the test vessels and additional calcium carbonate solids or grout solids were added to the test vessels. Calcium carbonate solids were utilized as a grout-representative phase in the oxidizing test samples (Oxidizing Regions II and III) and in one reducing test sample (Reducing Region II). These additions were made to the test samples under the appropriate gaseous atmospheres (nitrogen for reducing cases and CO₂-stripped air for oxidizing cases). Utilizing this single reagent (CaCO₃) to represent the grout solids simplified the system and allowed for better control of the solution pH and E_h.

Cement, Fly Ash, and Slag (CFS) grout solids were used rather than calcium carbonate reagent in one Reducing Region II test sample. The CFS solids were initially prepared as a monolith following the grout recipe utilized to fill SRS Tank 18. The recipe included 125 parts of Cement Type I/II, 210 parts of Slag Grade 100, and 363 parts of Fly Ash Class F. Sand was not added as a component of the monolith since both fly ash and slag contain significant quantities of silicon. Prior to contact with the infiltration water simulant, the CFS monolith was broken into pieces which were then crushed and sieved through a 100 mesh sieve. The CFS powder was stored and transferred into the shielded cells in small vials containing no head space volume in order to minimize air exposure of the grout. CFS or calcium carbonate solids were added to each test sample at a concentration of 16.7±0.1 g/L slurry. FeS solid was added to reducing samples at a concentration of 3.1-3.2 g/L slurry. Total slurry volumes ranged from 200-250 mL.

An archived sample of residual radioactive sludge solids retrieved from the floor of SRS Tank 18 prior to tank closure was utilized for leach testing. The sludge sample composition is summarized in Tables III (elemental) and IV (radionuclide) based on analysis conducted by Oji [5]. Tank 18 solids were added to each test sample at a concentration of 30.1±0.2 g/L slurry. This phase ratio was selected based on a combination of solubility and analytical limit of detection considerations and not the actual condition in a grout-filled tank. A goal in selecting the phase ratio was ensuring that key dose contributors were not removed to any appreciable extent by the pore water flow prior to reaching the final tank aging condition (Oxidizing Region III).

TABLE III. Major Tank 18 Residual Sludge Elemental Components as Reported by Oji [5].

Element	Wt. %
Al	11.0
Ca	2.9
Fe	9.8

Mg	3.8
Mn	1.0
Si	2.2
U	6.3

Table IV. Selected Tank 18 Residual Sludge Radionuclide Components as Reported by Oji [5].

Radionuclide	μCi/g
Tc-99	2.7E-02
Th-229	1.9E-05
Th-230	1.4E-04
U-233	1.2E-03
U-234	2.0E-02
Np-237	9.1E-03
U-238	2.0E-02
Pu-239	1.6E+01
Pu-240	3.6E+00
Pu-241	1.6E+01
Am-241	7.5E+00
Cm-244	1.2E-01

Both pH and ORP data were measured with a dual channel Thermo Scientific Orion Star Series meter. Slurry pH data was collected during leach testing using a sealed, double-junction Oakton pH Electrode with an Epoxy body. The pH meter was calibrated prior to each use with pH 4, 7, and 10 standard buffer solutions. E_h data was collected using a Thermo Scientific 9179BN Low Maintenance ORP Triode with an Epoxy body. The E_h probes were checked using Thermo Scientific Oxidation-Reduction Potential (ORP) Standard 967901. The ORP standard was checked once during each series of sample measurements and the standard data ranged from +218 to +222 mV (E_h range: +418 to +422 mV) during testing. All reported sample E_h values are relative to the Standard Hydrogen Electrode (SHE). A standard correction of +200 mV was applied to all ORP data to convert the data to E_h format, based on the manufacturer instructions and data obtained for the ORP standard.

Since the oxidizing sample types represent grout aging stages where many volumes of pore water have passed through the system, these samples were washed with two portions of the appropriate simulant solutions prior to the initiation of leaching studies. Scoping studies indicated that the wash volumes used would decrease the soluble sodium concentration to near that of the as-prepared simulant composition.

The reducing samples were not washed initially, since this condition represents the early portion of grout aging. However, after approximately three weeks of leach testing, the liquid was decanted from each of the reducing samples and fresh simulant was added. As a result, testing under reducing conditions was conducted in two phases with the second testing phase involving lower solution ionic strength. Leach test samples were monitored during testing to confirm that evaporative or entrainment sample losses associated with continuous sample gas purging were not significant. During the entire course of the leaching studies, 30-50 volume percent of the initial sample slurries was consumed due to sub-sampling. During testing, an air purge (without CO₂ removed) was periodically utilized to lower the pH of the Oxidizing Region III samples, as needed to adjust the pH to near the target values. Additional calcium hydroxide reagent was added as needed during testing to raise the sample pH.

Sample aliquot volumes of 5-13 mL (depending on the volume needed for analysis) were collected from the leaching test vessels for analysis after the measurement of the solution pH and E_h at approximately weekly intervals. Seven sampling events were conducted over a period of nearly two months (sub-sample collection days: 9, 16, 23, 27, 37, 44, and 51). The aliquots were filtered as described above through 0.1- μ m polyvinylidene difluoride (PVDF) syringe filter units without opening the analysis bottle caps. Blank sample analyses generally indicated that contamination from the cell environment was minimal for all metals analyzed, although uranium was observed in some sample blanks at relatively low levels.

Each sample received an addition of 0.5-1.5 mL of 5 M nitric acid (adjusted for the target sample volume to give a sample:acid volume phase ratio near 8) to acidify the samples and avoid post-filtration precipitation. Aliquots of the acidified samples were analyzed for plutonium by alpha spectroscopy following separation using thenoyltrifluoroacetone (TTA) and for uranium, technetium, and neptunium by Inductively Coupled Plasma Mass Spectrometry (ICP-MS). Reported plutonium concentrations are based on the measured combined Pu-239/Pu-240 concentrations in dpm/mL converted to molar concentrations assuming 100% Pu-239. Pu-238 concentrations were negligibly small (on a molar concentration basis) for all samples. Additional experimental details are reported separately [6].

RESULTS AND DISCUSSION

Leaching studies were conducted with actual SRS Tank 18 residual solids and grout-representative solids in pore water simulants under controlled atmosphere conditions targeting pH and E_h values representing three aging periods following tank closure. Testing was continued for approximately two months with weekly pH/E_h measurement and sample collection. The average pH, E_h, and metal concentrations (data averages from final 2-4 weeks) observed for each test sample are provided in

Table V. These concentrations were observed in the final weeks after testing following the sample washing that occurred during leach test initiation (oxidizing samples) and after the first few weeks (reducing samples). During testing, the Oxidizing Region III-D sample was inadvertently flooded with water from the bubbler system. As a result, this sample was exposed to a larger total wash volume. This exposure resulted in lower leachate metal concentrations for this sample than were observed for the replicate Oxidizing Region III-C sample, as discussed below.

The target pH values were achieved to within 0.5 pH units for all samples and an E_h range of approximately 0.7 V was observed for the final samples. For most test samples, steady-state pH and E_h data were observed during the final 2-3 weeks of testing. The lowest and highest E_h values observed after sample stabilization of ~ -0.2 V and $\sim +0.5$ V were significantly less negative and less positive, respectively, than the target values (Table I). These findings are consistent with previous tests with simulated Tank 18 sludge solids and are the result of the presence of multiple solid phases and complex solution chemistry. Based on the previous testing, achievement of more negative and more positive E_h values would require the addition of non-representative reductants and oxidants, respectively.

Leachate uranium concentrations for each sample were higher by several orders of magnitude than all other metals. The maximum uranium concentration of $4E-4$ M was observed for the Oxidizing Region III-C sample. Presumably due to excessive washing (and removal of uranium), the uranium concentration for the Oxidizing Region III-D sample was significantly lower than the replicate -C sample. Intermediate uranium concentrations were observed for the Oxidizing Region II samples (-A and -B) while the lowest uranium concentrations ($2E-6$ M) were observed for the Reducing Region II samples. The uranium concentrations observed versus time for the Oxidizing Region II-B sample were not stabilized at test conclusion while concentrations of other samples were generally stable.

Table V. Post-wash pH, E_h , and Metal Concentrations for Each Pore Water Test Condition Using Actual Tank 18 Residual Solids.

Test Sample	Additives	Atmosphere	E_h^a (mV)	pH ^a	U ^{a, c} (M)	Np ^b (M)	Pu ^a (M)	Tc ^a (M)
Oxidizing Region II-A	Ca(OH) ₂ , CaCO ₃	air	+351	11.2	4E-6	<2E-10	4E-10	1E-8
Oxidizing Region II-B			+328	10.8	2E-5	3E-10	6E-9	1E-8
Oxidizing Region III-C	CaCO ₃	air (with/ without CO ₂)	+520	9.4	4E-4	4E-9	1E-8	1E-8
Oxidizing Region III-D			+493	9.3	7E-5	1E-9	6E-9	6E-9
Reducing Region II-E	Ca(OH) ₂ , CaCO ₃ , FeS	nitrogen	-208	10.9	2E-6	<2E-10	2E-9	<6E-10
Reducing Region II-F	CFS ^d , FeS		-196	11.4	2E-6	<2E-10	7E-11	<6E-10

^a average data from final 4 weeks

^b average data from final 2-3 weeks

^c due to nearly complete U dissolution observed during washing these leachate concentrations may not represent saturation

^d CFS = cement, flyash, and slag grout solids

The initial leachate solutions for the Reducing Region II samples were decanted from the test vessels after approximately three weeks of contact in order to provide two sets of results representing the early portion of this aging period where higher ionic strength is expected and the later portion with lower ionic strength. Much higher uranium concentrations were observed for the reducing samples during the first contact phase than those reported in Table V from the second phase. The uranium concentrations for the first contact phase ranged from 1E-5 M for the Reducing Region II-F sample to 7E-4 M for the Reducing Region II-E sample. The lower concentration observed for the Reducing Region II-F sample is presumably associated with the CFS solids and indicates that the presence of grout solids results in lower leachate uranium concentrations during this early phase of tank aging. Significantly lower uranium concentrations (2E-6 M) were observed following decantation of the first leachate solution (as shown in Table V). It is unknown whether this difference is associated with ionic strength differences between the first and second leachates or is associated with variability in the uranium speciation and accessibility within the sample.

Surprisingly, the control sample analysis indicated that uranium contamination occurred for the later control samples. However, the highest uranium concentration in the control samples of 1E-7 M is significantly lower than all leach test sample concentrations observed.

For oxidizing test conditions, the Tank 18 samples were washed with pore water simulants prior to initiating the leaching tests. As shown in Table VI, higher metal concentrations were observed for the wash solutions than were observed for any leach test sample and the concentrations of uranium, neptunium, and plutonium significantly exceeded the maximum predicted values in the PA. Mass balance calculations based on these concentrations indicated that nearly all of the uranium from the Oxidizing Region III test samples dissolved during the washing step. However, <20% of each of the other metals dissolved. These results indicate that it is possible to exceed the observed leachate concentrations shown in Table V during initial pore water contacts.

Significant uranium solubility is typically observed in tank sludge wash solutions and commonly observed uranium crystalline sludge phases include Clarkeite, $\text{Na}((\text{UO}_2)\text{O})(\text{OH})\cdot\text{H}_2\text{O}$, and sodium diuranate, $\text{Na}_2\text{U}_2\text{O}_7\cdot 6\text{H}_2\text{O}$ [7, 8]. The Tank 18 residual sample used for testing included both the Clarkeite uranium phase and a uranium carbonate phase, Cejkaite, $\text{Na}_4\text{UO}_2(\text{CO}_3)_3$, not previously observed in other tank waste samples [9]. Carbonate phases such as Cejkaite would be expected to be more soluble than typical oxide phases. A review of the Tank 18 processing history prior to closure indicated that the conditions favored the formation of carbonate complexes of the actinide metals [10]. Due to the uranium losses to the wash and the near depletion of uranium from the samples, the uranium concentrations reported for the oxidizing samples are not believed to represent solubility limits. Carbonate phases of the other actinide metals with higher solubility may have also formed, but the observation of these minor phases by X-ray Diffraction (XRD) analysis would be unlikely.

Leachate neptunium concentrations were 4-5 orders of magnitude lower than the uranium concentrations observed under the same conditions. The maximum neptunium concentration of 4E-9 M was observed for the Oxidizing Region III-C sample. Lower than detectable amounts of neptunium (<2E-10 M) were observed for the Reducing Region II samples (during both the first and second simulant contacts) and the Oxidizing Region II-A sample. Neptunium activity levels in the original sample (Table IV) on a curie basis were lower than any of the four radionuclides analyzed, but mass balance calculations indicate that only a small percentage of the total neptunium dissolved during testing. No control samples analyzed contained neptunium above detectable levels.

Table VI. Metal Concentrations Observed for ORII-A and ORIII-C Wash Solutions.

Test Sample	U (M)	Np (M)	Pu (M)	Tc (M)
Oxidizing Region II-A	3.2E-04	1.3E-09	4.0E-08	1.0E-08
Oxidizing Region III-C	4.6E-03	2.9E-08	3.0E-07	9.4E-09

The maximum plutonium concentration of $1\text{E-}8$ M was observed for the Oxidizing Region III-C sample. A gradual increase in Pu concentration was observed during testing for both Oxidizing Region II test samples versus time (results not provided), and it is unclear based on the data whether saturation and equilibrium were achieved for these samples during the testing period. In addition, the Pu concentrations observed for the Oxidizing Region II-A sub-samples were consistently an order of magnitude lower than the -B samples. This difference is not understood, since nearly identical sample preparation methods and amounts were used for each sample. The lowest plutonium concentrations were observed for the Reducing Region II samples with the sample containing CFS solids (-F) exhibiting much lower soluble plutonium levels ($7\text{E-}11$ M) than the sample containing calcium carbonate solids (-E sample; $2\text{E-}9$ M Pu). As was observed for the uranium samples, this result indicates that the presence of grout solids may serve to inhibit plutonium leaching into the pore water. In contrast to uranium, plutonium leachate concentrations were not elevated in the first contact phase under reducing conditions (results not provided).

Only one control sample contained plutonium above detectable limits. This control sample contained plutonium at levels just above detection and well below most leach test sample results. This observation indicates that the test methodology and sub-sample design successfully eliminated plutonium contamination and the plutonium concentrations observed for the samples can be attributed to the metal leaching from the Tank 18 residual solids.

The highest leachate technetium concentration of $1\text{E-}8$ M was observed for both Oxidizing Region II and III samples (-A through -C). Analysis and mass balance calculations for the wash solutions indicate that 17% of the technetium may have been lost from these samples during washing. The data trends in the technetium concentrations for the oxidizing samples indicate that the technetium concentration did not stabilize during testing but continued to gradually increase. Lower than detectable amounts of technetium ($<6\text{E-}10$ M) were observed for the Reducing Region II samples during the second simulant contact and for the control samples. Detectable, but low, technetium concentrations ($\leq 1\text{E-}08$ M) were observed in the leachate solutions for the first simulant contact under reducing conditions.

To support PA modeling of the closed waste tank, metal solubilities were calculated by Denham [4] for pure metal oxide phases under oxidizing conditions assuming equilibrium with dissolved oxygen, as well as under non-equilibrium conditions, which is believed to be more realistic. Solubility predictions were calculated for the pure metal oxide phases under these conditions and apparent solubilities were calculated for the metals co-precipitated with Fe sludge phases. The apparent solubilities are based on the primary iron phase solubility and the ratio of the metals of interest to the iron phase. The predicted apparent solubilities for the co-precipitated phases were much lower than the solubilities for the pure phases.

In general, the predicted metal concentrations for co-precipitated phases are all lower than were experimentally observed [4]. Thus we conclude that a significant fraction of the Tank 18 residual solids sample used in this testing appears to be pure metal oxide phases and not co-precipitated phases. Uranium concentrations observed under oxidizing conditions exceeded the maximum predicted values, indicating that the uranium speciation in the Tank 18 residuals may be dominated by a more soluble species (such as a carbonate phase) than assumed in the PA modeling. Maximum neptunium and plutonium concentrations did not exceed the predicted values for the cases where dissolved oxygen is assumed. Data trends for technetium indicated that equilibrium and saturation had not been achieved. No solubility limit was reported by Denham for technetium under oxidizing conditions, due to the high solubilities of oxidized forms of technetium. It was assumed in the PA modeling that the metals (in particular technetium) in the tank residuals were initially present as low solubility forms in order for them to remain in the waste after tank washing. It was assumed during leaching that technetium was either co-precipitated with iron, making it very insoluble, or that (under oxidizing conditions) it would be instantaneously soluble and easily leached. The experimental results are consistent with the presence of reduced technetium that is resistant to re-oxidation.

CONCLUSIONS

Leaching studies were completed for actual SRS Tank 18 residual solids using customized test equipment and a sub-sampling system and sample handling methodology designed to minimize or eliminate sample contamination from the SRNL shielded cells test facility. Low leachate neptunium, plutonium, and technetium concentrations (near analytical detection limits in some cases) were observed for the Tank 18 samples and blank sample metal concentrations were below detectable limits in most cases, confirming the suitability of the testing approach. After washing, the concentrations of neptunium, plutonium, and technetium observed in leachate solutions were near or slightly below the maximum predicted concentrations utilized for PA modeling, although trends in the technetium data indicate that equilibrium and saturation were not achieved during the 2-month testing period. Observed uranium concentrations were high and significantly exceeded predictions, presumably due to differences between the actual and assumed chemical speciation. After test conclusion, it was discovered that significant losses of uranium to the wash solutions occurred for oxidizing samples and that the concentrations of uranium, neptunium, and plutonium were higher in the wash solutions than in any leachate samples analyzed. The metal concentrations in the wash samples also exceeded the maximum predicted concentrations assumed and utilized for PA modeling. This was an unexpected result and is presumably associated with the presence of more soluble chemical forms of these metals (as confirmed for uranium by XRD). Due to the uranium losses to the wash and the near depletion of uranium from the samples, the

uranium concentrations reported for the oxidizing leachate samples are not believed to represent solubility limits. Despite the discovery of high metal concentrations in the wash solutions, the measured leachate concentrations for the remaining metals (neptunium, plutonium, and technetium) are believed to be representative of the concentrations that might be observed during the major portion of the tank aging time periods of interest. The new data from the Tank 18 leaching studies is not expected to significantly impact predicted doses from the release of radionuclides into the environment from the closed waste tank based on solubility assumptions used in previous Performance Assessment modeling [11].

Additional conclusions based on the test results regarding neptunium, plutonium, and technetium leaching from Tank 18 residual solids are provided below.

- The results revealed that neptunium is less soluble than expected, indicating that this metal is reduced in the waste to a form that resists re-oxidation and is relatively insoluble, even under oxidizing conditions.
- The results indicate that plutonium might not be as insoluble as expected, but the solubility under oxidizing conditions will not exceed the maximum values calculated for plutonium oxide phases in equilibrium with dissolved oxygen. Prior to the Tank 18 residual waste testing there was also a concern that plutonium might exist as a much more soluble carbonate phase. The solubility of the plutonium carbonate phase, $\text{Pu}(\text{OH})_2\text{CO}_3$, under ORII conditions was calculated to be $4.8 \text{ E-}5 \text{ M}$ [10], which is 4-5 orders of magnitude larger than the observed solubility.
- The results indicate that technetium might not be as insoluble as expected. It was assumed in the PA that technetium would either be co-precipitated with iron, making it very insoluble, or would (under oxidizing conditions) be instantaneously soluble and easily leached. The waste release testing results for oxidizing conditions are close to the solubility calculated for reduced technetium ($\text{TcO}_2 \cdot 1.6\text{H}_2\text{O}$) of $1\text{E-}8 \text{ M}$. Studies indicate that Tc(VI) reduced by Fe(II) in the presence of Fe(III) solids forms a solid Tc(IV) phase which resists re-oxidation and has an apparent solubility near that of $\text{TcO}_2 \cdot 1.6\text{H}_2\text{O}$ [12]. The reduction of technetium by Fe(II) may have occurred in Tank 18 causing much of the Tc in the sludge to be reduced. The experimental results are consistent with the presence of reduced technetium that is resistant to re-oxidation.

REFERENCES

1. "Performance Assessment for the H-Area Tank Farm at the Savannah River Site", SRR-CWDA-2010-00128, Rev. 1, November 2012.
2. D. H. Miller, K. A. Roberts, K. M. L. Taylor-Pashow, and D. T. Hobbs, "Determining the Release of Radionuclides from Tank Waste Residual Solids", SRNL-STI-2014-00456, Rev. 0, September 2014.
3. W. D. King and D. T. Hobbs, "Determining the Release of Radionuclides from Tank Waste Residual Solids: FY2015 Report", SRNL-STI-2015-00446, Rev. 0, September 2015.
4. M. E. Denham and M. R. Millings, "Evolution of Chemical Conditions and Estimated Solubility Controls on Radionuclides in the Residual Waste Layer during Post-Closure Aging of High-Level Waste Tanks", SRNL-STI-2012-00404, Rev. 0, August 2012.
5. L. N. Oji, D. Diprete, and C. J. Coleman, "Characterization of Additional Tank 18 Samples", SRNL-STI-2010-00386, Rev. 0, September 2010.
6. W. D. King and D. T. Hobbs, "Determining the Release of Radionuclides from Tank 18 Waste Residual Solids: FY2016 Report", SRNL-STI-2016-00432, Rev. 0, August 2016.
7. W. D. King, T. B. Edwards, D. T. Hobbs, W. R. Wilmarth, "Solubility of Uranium and Plutonium in Alkaline Savannah River Site High Level Waste Solutions", Separation Science and Technology, Vol. 45, pp. 1793–1800 (2010).
8. W. D. King and M. S. Hay, "Alternative Enhanced Chemical Cleaning: Basic Studies Results FY09", SRNL-STI-2009-00791, Rev. 0, February 2010.
9. M. S. Hay, P. E. O'Rourke, and H. M. Ajo, "Scanning Electron Microscopy and X-Ray Diffraction Analysis of Tank 18 Samples", SRNL-STI-2012-00123, Rev. 0, March 2012.
10. D. T. Hobbs, "Form and Aging of Plutonium in Savannah River Site Waste Tank 18", SRNL-STI-2012-00106, Rev. 0, February 2012.
11. M. H. Layton, "Evaluation of Waste Release Testing Results against the Tank Farm Performance Assessment Waste Release Model", SRR-CWDA-2016-00086, Rev. 0, August 2016.
12. J. M. Zachara, S. M. Heald, B. Jeon, R. K. Kukkadapu, C. Liu, J. P. McKinley, A. C. Dohnalkova, D. A. Moore, "Reduction of Pertechnetate [Tc(VII)] by Aqueous Fe(II) and the Nature of Solid Phase Redox Products", *Geochimica et Cosmochimica Acta* 71 (2007) 2137.